

Veroni Pak

Polyolefin
VerCAST films

WHAT CHARACTERIZES VERCAST FILMS?

- High transparency and gloss
- High mechanical strength
- Excellent sealability
- One-sided treatment
- Approved for contact with food



Types of VerCAST films

For bread packaging	For freezing	For deep freezing	For lamination	Special films
BW – basic version	F(A) – basic version	SF – with excellent resistance to low temperatures	L – colorless, transparent	AF – with antifog effect
BW(S) – with higher seal temperature	F(AS) – with higher seal temperature	EF – polyethylene, with higher transparency	Lw – white, non-transparent	CC – without sealable layers
BS – stiffer, with higher transparency	F – flexible, with higher resistance to tear and rupture	SF/EF BIO – made with materials derived from renewable sources	Lw(a) – white, with lower seal temperature	M – microperforated
				S – for sterilization

VerCAST EF BIO

TECHNICAL DATASHEET

Veroni
Pak

Requirements	Nominal/guaranteed value												Test method
Thickness [um]; ± 6%	20-24	25-29	30-34	35-39	40-44	45-49	50-54	55-59	60-64	65-69	70-74	75-79	ISO 4593
Tensile strength [N/mm2] - lengthwise (MD), not less than - widthwise (TD), not less than	32 19			30 17			28 15						ISO 527-1, -3
Elongation at break [%] - lengthwise (MD), not less than - widthwise (TD), not less than	480 650	500 670	520 690	540 710	560 730	580 750							
Coefficient of friction, (film/film) NT/NT; not more than	0,20												ISO 8295
Haze [%], not more than	3,0	3,1	3,2	3,3	3,4	3,5	3,6	3,7	3,8	3,9	4,0	4,1	ASTM D 1003
Gloss(45°) [%], not less than	75												ASTM D 2457
Treatment [mN/m], not less than	36												ISO 8296
Lamination and print suitability	yes												MW/Veroni-Pak/01
Sealability	yes												MW/Veroni-Pak/02

Assessment of the suitability of the film for printing and lamination is carried out using a test fluid and is guaranteed for a period of 3 months from the manufacturing date indicated on the label attached to every roll. Other parameters listed above are guaranteed for a period of 6 months from the manufacturing date, nonetheless it is recommended to use the film within the first 3 months after the production when it retains its best properties.

IMPORTANT: If the film is transported and stored at temperatures below 15°C, it is advised to season the film at temperatures ≥ 20 °C for a minimum of 24h before further processing. It is recommended to process the film in the following conditions: temperature: 15 - 35°C, humidity: 50 - 75% Rh. Compliance with these conditions ensures stated properties of the film and its trouble-free processing.

The technical parameters stated in the table above are based on laboratory tests and are for informative purposes only. Veroni-Pak reserves the right to make changes to stated parameters. It is possible to produce films in thicknesses other than those specified in the table above. All the parameter values in the above table apply only to unprocessed film.

It is necessary to validate the film at every stage in the actual processing conditions. It is recommended to validate the film as a ready-made packaging under conditions of its final usage.

The film is fully recyclable.



Packaging Materials

Edition 3.

Date of issue: 28.09.2022

Veroni
Pak

VERONI Sp. z o.o.

Towarzystwa Jaszczurczego 10
87-200 Wąbrzeźno, Polska/Poland
NIP [VAT-ID]: PL8781805285



www.veroni-pak.com.pl